



ÇİMENTO SANAYİ ve TİCARET A.Ş.
MERSİN

P.K.614 YENİTAŞKENT TEL : 324 454 00 60(12)
FAX : 324 454 00 75 (2) 33013 MERSİN-TÜRKİYE
E.Mail : e.tozoglu@cimsa.com.tr

CEMENT ANALYSIS REPORT

EC Certificate of Conformity
Certificate No. 0086 - CPD - 458580

SAMPLE : White Portland Cement (Average Analysis)		STANDARD :EN 197-1 CEM I 52,5 N		
DATE OF REPORT : 01.05.2009				
CHEMICAL REQUIREMENTS	Results	Methods	Standart Values	
			Min.	Max.
Loss On Ignition %	3,24	EN 196-2	-	5,00
Insoluble Residue %	0,14		-	5,00
Sulfur Trioxide %	3,65	XRF	-	4,00
Soluble Chromium Cr ⁺⁶ ppm	0,84	AAS	-	-
Chloride %	0,0085	EN 196-21	-	0,10
PHYSICAL REQUIREMENTS				
Degree of Whiteness %	85,1	CIE system, Y value	-	-
Initial Setting Time Minute	105	EN 196-1,3	45	-
Soundness,Le Chatelier mm	1,0		-	10,0
2 Days Compressive Strength Mpa	36,0		20,0	-
28 Days Compressive Strength Mpa	60,0		52,5	-

Report shall not be reproduced except in full without the written approval of the testing laboratory.

A.T. / M.Y.

QUALITY CONTROL MANAGER

ÇİMSA
ÇİMENTO SANAYİ VE TİCARET A.Ş.
TOROSLAR MAH. TEKKİ ÇADDESİ
YENİTAŞKENT MERSİN
URAY Y.D. 327 002 8245
M. Erkin TOZOGLU